WE CLAIM:

1. A method for removal of post reactive ion etch sidewall polymer rails on a Al/Cu metal line of a semiconductor or microelectronic composite structure comprising:

supplying a mixture of an etching gas and an acid neutralizing gas into a vacuum chamber in which said composite structure is supported to form a water soluble material of sidewall polymer rails left behind on the Al/Cu metal line from the RIE process; removing the water soluble material with deionized water; and removing photo-resist from said composite structure by either a water-only plasma process or a chemical down stream etching method.

2. The method of claim 1 wherein said composite structure comprises a silicon oxide interlayer dielectric, a barrier layer, a metal stack layer, and a photoresist layer.

3. The method of claim 2 wherein said etching gas is HF and said acid neutralizing gas is NH_3.

4. The method of claim 3 wherein removing said photo-resist accomplished at temperatures greater than 200°C.

5. The method of claim 1 wherein said mixture of said etching gas and said acid neutralizing gas is in the form of a plasma.

6. A method for removal of post ion etch sidewall polymer rails on a Al/Cu metal line of a semiconductor or microelectronic composite structure comprising:

forming a water-only plasma process to strip the photo-resist layer of a semiconductor or micro-electronic composite structure previously subjected to a RIE process;

supplying a mixture of an etching gas and an acid neutralizing gas into a vacuum chamber on which said structure is supported to form a water soluble material of sidewall polymer rails left behind on the Al/Cu metal line from the RIE process; and

removing the water soluble material with deionized water.

7. The process of claim 6, wherein the water-only plasma process is conducted at temperatures between about 175-275°C to limit the thickness of the sidewall polymer.

8. The process of claim 7 wherein said composite structure comprises a silicon oxide interlayer dielectric, a barrier layer, a metal stack layer, and a photo-resist layer.

9. The process of claim 8 wherein said etching gas is HF and said acid neutralizing gas is NH_3.

10. The process of claim 6 wherein said mixture of said etching gas and said acid neutralizing gas is in the form of a plasma.

11. An integrated metal etch tool operable to perform the method as recited in claim 6.

12. An integrated metal etch tool operable to perform the method as recited in claim 7.

add a'7
add b'7

09204706 . 120398